

Sandblast Slags
Foundry Sands
Empire Blast Equipment
Bullard Safety Equipment
Sandblast Hose & Nozzles
Walnut Shells & Corn Cob Grit
Waterjet & Sandblast Garnet
Schmidt Blast Equipment
Silica Free Abrasives
Steel Shot & Grit
Aluminum Oxide
Glass Beads

#25 WHITE LIGHTNING (Nepheline Syenite)

TYPICAL SCREEN ANALYSIS

U.S. SIEVE	% RETAINED
20 Mesh	0.4%
25 Mesh	8.9%
30 Mesh	35.0%
40 Mesh	53.4%
Pass 40 Mesh	2.4%
Effective size	0.45 mm
Uniformity Co-Efficient	1.39

TYPICAL CHEMICAL ANALYSIS

*Silicon Dioxide (SiO ₂)	60.20%
Iron Oxide (Fe ₂ 0 ₃)	0.15%
Aluminum Oxide (Al ₂ O ₃)	23.40%
Calcium Oxide (CaO)	0.40%
Magnesium Oxide (MgO)	0.02%
Potassium Oxide (K ₂ O)	5.00%
Sodium Oxide (Na ₂ O)	10.40%
Loss on Ignition (LOI)	0.41%

Colour:

White with some Black Specks

Grain Shape:

Angular

Bulk Density:

92-95 lbs./ft³

All products are sold without warranty expressed or implied and seller specifically does not warrant that these products are suitable for a particular purpose or purposes or are merchantable. Buyer agrees it does not rely on seller's skill or judgment to select or furnish these products. Buyer shall make its own tests to determine that suitability of such product for its purposes. July 2019

Tel: (905) 527-6000

Toll Free Tel: 1-888-794-5665

Fax: (905) 527-6660

Toll Free Fax: 1-888-794-7263

info@allredi-ca.com

^{*}Exists in a complex silicate of Albite, Microline and Nepheline. There is no free silica present.